

Product Data Sheet

Tomoil™ Quenching Oil 220

Quench oil

Product description

Tomoil™ Quenching Oil 220 represents a high-quality quenching fluid specifically designed for the heat treatment of ferrous metals in diverse quenching processes. Its formulation is tailored to enhance profound and uniform hardening, effectively tackling issues of distortion and cracking, and guaranteeing a polished surface quality.

Application

Tomoil™ Quenching Oil 220 is recommended for the conventional and fast quenching of ferrous metals, such as carbon steel, gray iron, and alloy steel.

Features & Benefits

- Controlled cooling rate to minimize cracking and distortion
- Achieves a good surface finish
- Demonstrates excellent oxidation resistance and thermal stability
- Low volatility reduces oil loss through vaporization

Typical Properties

Property	Unit	Test method	Typical value
ISO viscosity grade	-	-	220
Density at 15°C	g/cm ³	ASTM D4052	0.897
Kinematic Viscosity at 40°C	cst	ASTM D445	220.0
Kinematic Viscosity at 100°C	mm ² /s	ASTM D445	18.69
Viscosity Index	-	ASTM D2270	94
Flash Point (COC)	°C	ASTM D92	266
Pour Point	°C	ASTM D97	-9

Typical property characteristics are based on current production. Whilst future production will conform to TomoilTM specifications, variations in these characteristics may occur.

Performance claims

- ISO 6743-14 L-UHA
- ISO 6743-14 L-UHB

Health, Safety & Environment

- **Health and Safety**

This product is unlikely to present any significant health or safety hazard when properly used in the recommended application, and good standards of industrial and personal hygiene are maintained.

For further guidance on Product Health & Safety refer to the appropriate Safety Data Sheet which can be obtained upon request or through our website: www.tomoil.de

- **Protect the Environment**

Take used oil to an authorized collection point. Do not discharge into drains, soil or water.

Available pack sizes

- | | |
|-------------------------|--------------------------|
| • 20 L Canister plastic | • 200 L Drum sheet metal |
| • 30 L Canister plastic | • 1000 L Container |

Storage

- We recommend to store all packages under cover.
- Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings.
- Products should not be stored above 60 °C, exposed to hot sun or freezing conditions.

Notes

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by ALCO LLC for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our sales specialists if you require any further information.

